

A251

VOID SECURITY LABEL | TOTAL TRANSFER

Description

Traces of prints or patterns are totally transferred to substrates when the tape is removed. Excellent tamper evident performances.

Carrier	PET
Color	Red, Blue, White, Black
Adhesive	Rubber synthetic
Liner	White double PE single silicon glassine paper

VOID temperature	Temperature: -10°C - +40°C; Relative humidity: 55% +/- 10%
Operation temparture	+10°C - +35°C
VOID message	VOID

Physical data

180°C Peel Adhesive for VOID	0.20-0.98N/2,5cm	PSTC-1
Total thickness	0.070-0.080mm	
Initial tack	< 10cm	PSTC-6 #14 ball
Holding power	0.5kg/25mm x 25 mm	>24hrs PSTC-7
Holding power for temperature resist 60°C	0.5kg/25mm x 25mm	>3hrs PSTC-7

Characteristics

The product is specifically designed to overcome problems often associated with security seals on carton or paper surfaces giving a clean crisp sharp result. Upon peeling the adhesive leaves a bold VOID tekst on top of the surface being protected.

Application

Widely used for sealing documents, gifts seal, medical packaging or any product in need additional protection en route to client, PE shrinking film, high value 3C products box seals, mail order goods shipping, cooked food packaging delivery, ballot paper seals, event admission tickets, signature seal, RFID label, confidential medical document pouches, legal pouch and envelope seals.

Shelf life

1 year under normal condition. Avoid exposing to high humidity and direct sunlight.

How to apply

When applying the tape the surfaces to be bonded should be dry, dust & grease free and thoroughly clean. Avoid touching the exposed adhesive surface of the tape as this impairs the performance. The adhesive used on these tapes are pressure sensitive, so always ensure sufficient pressure is applied to the tape evenly over the whole surface to ensure the best bonding results.

Certificates**REACH**

Please contact Altec for the latest REACH document available.

RoHS

Please contact Altec for the latest RoHS document available.

Disclaimer:

Values shown in this document are averages only. For legal reasons, we emphasize that the information on this data is available as is and that Altec gives no guarantees with respect to the accuracy and completeness nor with respect to interpretations made on the basis of this information.